
Optical Properties of Glass

Edited by
Donald R. Uhlmann
Norbert J. Kreidl

Published by The American Ceramic Society, Inc.
Westerville, OH

BEST AVAILABLE COPY

Library of Congress Cataloging-in-Publication Data

Optical properties of glass/edited by Donald R. Uhlmann, Norbert J. Kreidl.
p. cm.

Includes bibliographical references and index.

ISBN 0-944904-35-1 : \$86.00

1. Glass—Optical properties. I. Uhlmann, D. R. (Donald R.) II. Kreidl, N. J.

QC375.068 1991

620.1 '4495—dc20

91-24414
CIP

ISBN 0-944904-35-1

Copyright ©1991, The American Ceramic Society, Inc. All rights reserved.
No part of this book may be reproduced, stored in a retrieval system, or transmitted in
any form or by any means, electronic, mechanical, photocopying, microfilming, recording,
or otherwise, without written permission from the publisher.

Printed in the United States of America

1 2 3— 95 94 93 92 91

BEST AVAILABLE COPY

A comparison of the valence vibration bands for Si-O (9 μm), B-O (7.5 μm), and P-O (10.5 μm) agrees with Kreidl et al.'s⁴ finding that the replacement of SiO_2 by B_2O_3 causes a negative, that by P_2O_5 a positive deviation of the dispersion from the normal straight line.

Change of Dispersion by the Incorporation of Added Absorption Centers: Käs⁶ investigated the changes in dispersion on incorporation of absorption centers (λ_a) in the ir and uv. Since "normal" glasses generally absorb at λ_a below 0.3 μm , added centers of absorption were chosen at $\lambda \approx 0.35 \mu\text{m}$, that is, above 0.3 μm to affect dispersion, but below 0.4 μm to avoid coloration. The selection of suitable ions is based on ligand field theory. The following ions possess absorption bands between $\lambda_a = 0.3$ and 0.4.

Ion	Coordination	Absorption Band
Fe^{3+}	6 and 4	0.38
Ti^{4+}	6	0.37
V^{5+}	6	0.32
Cr^{6+}	4	0.36
Ag^0		0.34

Glasses may be doped with the ions, Ag^0 can be obtained by irradiation. Fe^{3+} is least suitable because it is usually accompanied by some Fe^{2+} whose absorption band near 1 μm induces color. Ti^{4+} was found to be best⁶ because it introduces no absorption in the visible nor near infrared. As early as 1965, Kreidl et al.⁴ affected dispersion by introducing cerium and recommended this technique for tailoring partial dispersion. The absorption edge of cerium is near 4 μm and may induce a slight yellow coloration.

To produce additional absorption bands, vibrating molecular groups would have to be introduced which will affect structure, uv absorption, and the location and intensity of the ir bands of the base glass. It is, therefore, difficult to predetermine the influence of added centers. For contemporary ir optics, however, a large variety of components affecting the ir edge are available.

Optical Glasses with Anomalous Partial Dispersion: The progress in high-quality optics achieved by the use of crystals with extreme partial dispersions has been known for a long time. The associated disadvantages such as cleavage in preferred direction, poor chemical resistivity, birefringence, low hardness, high cost, and so on had to be accepted in view of their favorable optical properties. In the past year a trend toward the development of glasses of equal or better partial dispersions than those of these crystals has been successful.

Besides a cruder characterization of optical glasses by their location in the $n_e - \nu_e$ diagram, it was Abbe who provided a finer characterization based on their partial dispersion behavior. For most glasses, Abbe's relation

$$P_{1,2} = a_{1,2} + b_{1,2} \nu_e$$

$$a_{1,2}, b_{1,2} \text{ constants, } \nu_e \text{ Abbe number} = \frac{n_e - 1}{n_F - n_C}; P_{1,2} = \frac{n_g - n_F}{n_F - n_C}$$